



Supplier of Welding Alloys

## Nickel Alloy Coated Electrodes

### Oxford Alloy® A

**SPECIFICATIONS**

AWS 5.11  
ASME SFA 5.11

**CLASSIFICATIONS**

AWS ENiCrFe-2  
UNS W86133

**DESCRIPTION / APPLICATION**

Oxford Alloy A electrodes are used for shielded-metal-arc welding of Incoloy® alloys 800 and 800HT, Inconel® alloys 600 and 601, and nickel steels. The weld metal of this electrode has excellent strength and oxidation resistance at high temperatures and retains impact resistance at cryogenic temperatures. Oxford Alloy A is an exceptional versatile product. This electrode can be used on a variety of austenitic and ferritic steels and nickel alloys. Some examples are combinations of stainless steels, carbon steels, Inconel® alloys, Incoloy® alloys, Monel® alloys, and copper-nickel alloys. Oxford Alloy A is especially useful for general maintenance welding of equipment exposed to strenuous service conditions. This electrode can be operated in all welding positions. The power supply is direct current, electrode positive.

INCONEL, INCOLOY and MONEL are trademarks of the Special Metal Group of Companies

AWS Chemical Composition						
Ni	C	Mn	Fe	S	Si	Cu
62.0 min	0.10 max	1.0- 3.5	12.0 max	0.02 max	0.75 max	0.50 max
Cr	Cb+Ta	Mo	P	OET		
13.0- 17.0	0.5- 3.0	0.5- 2.5	0.03 max	0.50 max		

**TYPICAL MECHANICAL PROPERTIES**

Tensile strength: 89,000 psi 610 MPa  
Yield strength: 72,000 psi 500 MPa  
Elongation: 36%

Please contact our sales department for more information at 800-562-3355 or 225-273-4800.

**Data contained in this publication are typical of the products and properties described, but are not suitable for specifications. OXFORD ALLOYS is a registered trademark of Oxford Alloys, Inc.**