



Supplier of Welding Alloys

Nickel Alloy TIG, MIG and SUB-ARC Wire

Oxford Alloy® 617

SPECIFICATIONS

AWS 5.14
ASME SFA 5.14

CLASSIFICATIONS

AWS ERNiCrCoMo-1
UNS N06617

DESCRIPTION / APPLICATION

Oxford Alloy 617 is used for the welding of Inconel® alloy 617. This filler metal is also used for joining various dissimilar high-temperature alloys because of its high temperature strength, oxidation resistance, and metallurgical stability. Some examples are Incoloy® alloys 800HT and 802 and cast alloys such as HK-40, HP, and HP-45 Modified.

INCONEL, INCOLOY and MONEL are trademarks of the Special Metals Group of Companies.

AWS Chemical Composition						
Ni	Cr	Co	Mo	Al	C	Fe
Bal	20.0-24.0	10.0-15.0	8.0-10.0	0.8-1.5	0.05-0.15	3.0 max
Mn	Si	S	Ti	Cu	P	OET
1.0 max	1.0 max	0.015 max	0.60 max	0.50 max	0.03 max	0.50 max

TYPICAL MECHANICAL PROPERTIES

Tensile strength: 112,000 psi 770 MPa
Yield strength: 88,500 psi 610 MPa
Elongation: 28%

Please contact our sales department for more information at 800-562-3355 or 225-273-4800.

Data contained in this publication are typical of the products and properties described, but are not suitable for specifications.
OXFORD ALLOYS is a registered trademark of Oxford Alloys, Inc.