



Techalloy 276

Description

Techalloy 276 is used for welding of materials of similar chemical composition (UNS Number N10276) , as well as dissimilar materials of nickel base alloys, steels and stainless steels. This wire can also be used for cladding steel with nickel-chromium-molybdenum weld metal.

This alloy, due to its high molybdenum content, offers excellent resistance to stress corrosion cracking, pitting and crevice corrosion.

Specifications & Approvals:

AWS A5.14 ERNiCrMo-4 UNS N10276 CWB

Typical Chemical Composition

C	Mn	Si	Fe	Cr	Mo	Ni	Nb	W	S	P	Al	Ti	Cu
.01	.55	.04	5.5	15.55	16.10	BAL		3.65	.002	.009			

Typical Mechanical Properties

Tensile Strength	105,000 PSI	720 MPA
Yield Strength	81,000 PSI	560 MPA
Elongation	40%	

Welding Parameters

Process	Diameter	Voltage	Amperage	Gas
TIG	.035" (0.9mm)	12-15	60-90	100% Argon
	.045" (1.2mm)	13-16	80-110	100% Argon
	1/16" (1.6mm)	14-18	90-130	100% Argon
	3/32" (2.4mm)	15-20	120-175	100% Argon
	1/8" (3.2mm)	15-20	150-220	100% Argon
MIG	.035" (0.9mm)	26-29	150-190	75% Argon + 25% Helium
	.045" (1.2mm)	28-32	180-220	75% Argon + 25% Helium
	1/16" (1.6mm)	29-33	200-250	75% Argon + 25% Helium
SAW	3/32" (2.4mm)	28-30	275-350	Suitable Flux may be used
	1/8" (3.2mm)	29-32	350-450	Suitable Flux may be used
	5/32" (4.0mm)	30-33	400-550	Suitable Flux may be used

Standard Packages:

MIG Wire– 33# wire basket	TIG Wire– 10# tube/30# Master Carton	SAW– 60# Coil
---------------------------	--------------------------------------	---------------