TECHALLOY® 418

Nickel • AWS ERNiCu-7

KEY FEATURES

- Used for TIG, MIG and SAW welding of copper alloys
- Dissimilar welding applications include joining Nickel 200 to copper-nickel alloys
- Q2 Lot® -Certificate showing actual deposit composition available online

WELDING POSITIONS

ΑII

CONFORMANCES

AWS A5.14M: 2011 UNS

ERNiCu-7 N04060

TYPICAL APPLICATIONS

Marine

SHIELDING GAS

MIG 75% Ar / 25% He **TIG** 100% Ar

DIAMETERS / PACKAGING

Diame in (ı	eter mm)	MIG 33 Ib (15 kg) Steel Spool	TIG 10 Ib (4.5 kg) Tube 30 Ib (13.6 kg) Master Carton	SAW 55 lb (25 kg) Coil
0.035	(0.9)	MG418035667		
0.045	(1.1)	MG418045667		
1/16	(1.6)	MG418062667	TG418062638	
3/32	(2.4)		TG418093638	SA418093726
1/8	(3.2)		TG418125638	SA418125726

WIRE COMPOSITION(1) - As Required per AWS A5.14M: 2011

WINE COM OSTITOR	713 Negative per 71003 713.1 4.101. 20 1 1						
	%C	%Mn	%Fe	%P	%S	%Si	
Requirements							
AWS ERNiCu-7	0.15 max	4.0 max	2.5 max	0.02 max	0.015 max	1.25 max	
Typical Performance(2)							
Techalloy® 418	0.07	3.0	0.1	0.002	0.002	0.31	
	%Cu	%Ni	%AI	%Ti	%Others		
Requirements							
AWS ERNiCu-7	Remainder	62.0 - 69.0	1.25 max	1.5 - 3.0	0.50 max.		
Typical Performance(2)							
Techalloy® 418	30	64	0.15	1.8	<0.50		

TYPICAL OPERATING PROCEDURES

Process	Diameter in (mm)	Voltage (volts)	Amperage	Gas
MIG	0.035 (0.9) 0.045 (1.1) 1/16 (1.6)	25-28 26-30 29-33	160-200 190-230 200-250	75% Argon / 25% Helium
SAW	3/32 (2.4) 1/8 (3.2)	28-30 29-32	275-350 350-450	Lincolnweld® P2000

⁽¹⁾ Typical all weld metal. (2) See test results disclaimer on pg. 13. Safety Data Sheets (SDS) are available on our website at www.lincolnelectric.com

Material Safety Data Sheets (MSDS) and Certificates of Conformance are available on our website at www.lincolnelectric.com

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application.

CUSTOMER ASSISTANCE POLICY

The Lincoln Electric Company is manufacturing and selling high quality welding equipment, consumables, and cutting equipment. Our challenge is to meet the needs of our customers and to exceed their expectations. On occasion, purchasers may ask Lincoln Electric for information or advice about their use of our products. Our employees respond to inquiries to the best of their ability based on information provided to them by the customers and the knowledge they may have concerning the application. Our employees, however, are not in a position to verify the information provided or to evaluate the engineering requirements for the particular weldment. Accordingly, Lincoln Electric does not warrant or guarantee or assume any liability with respect to such information or advice. Moreover, the provision of such information or advice does not create, expand, or alter any warranty on our products. Any express or implied warranty that might arise from the information or advice, including any implied warranty of merchantability or any warranty of fitness for any customers' particular purpose is specifically disclaimed.

Lincoln Electric is a responsive manufacturer, but the selection and use of specific products sold by Lincoln Electric is solely within the control of, and remains the sole responsibility of the customer. Many variables beyond the control of Lincoln Electric affect the results obtained in applying these types of fabrication methods and service requirements.

Subject to Change – This information is accurate to the best of our knowledge at the time of printing. Please refer to www.lincolnelectric.com for any updated information.

